

Ytterbium-Doped Single-Mode Single Clad Fiber



Nufern single-mode Yb-doped fibers are designed to support low power fiber lasers and amplifiers based on single-mode diode pump technology, rather than the multimode pumps used in high-power applications. For applications where high efficiency and very short device lengths are critical, these single-mode fibers are compatible with standard "telecom" fiber technology ensuring low splice loss to numerous fiber pigtailed components. The PM variety is designed with the PANDA-style stress structure which delivers linearly polarized light suitable for frequency conversion. These fibers make the ideal gain medium for low average power femtosecond fiber lasers and pre-amplifiers for higher power double-clad amplifiers.

Typical Applications

- Low power CW and pulsed fiber lasers
- Femtosecond fiber lasers
- Pre-amps for high-power, double-clad devices

Features & Benefits

- Single-mode output — Compatible with standard telecom 980/1060 nm fiber-based components
- PANDA-style stress structure — Linearly polarized output for frequency conversion
- High Ytterbium concentration — Short fiber lengths to reduce detrimental non-linear effects
- High slope efficiency (typically 75%) — Efficient utilization of pump power

Optical Specifications

	PM-YSF-LO	SM-YSF-LO	PM-YSF-HI	SM-YSF-HI
Operating Wavelength	1060 – 1115 nm	1060 – 1115 nm	1060 – 1115 nm	1060 – 1115 nm
Core NA	0.130	0.130	0.110	0.110
Mode Field Diameter	6.5 ± 1.0 μm @ 1060 nm	6.5 ± 1.0 μm @ 1060 nm	7.5 ± 1.0 μm @ 1060 nm	7.5 ± 1.0 μm @ 1060 nm
Cutoff	860 ± 70 nm	860 ± 70 nm	860 ± 70 nm	870 ± 60 nm
Core Attenuation	N/A	N/A	≤ 15.0 dB/km @ 1200 nm	≤ 15.0 dB/km @ 1200 nm
Core Absorption	25.0 ± 5.0 dB/m at 915 nm 80.0 dB/m at 975 nm	25.0 ± 5.0 dB/m at 915 nm 80.0 dB/m at 975 nm	85.0 ± 10.0 dB/m at 915 nm 250.0 dB/m at 975 nm	85.0 ± 10.0 dB/m at 915 nm 250.0 dB/m at 975 nm
Birefringence	2.5 × 10 ⁻⁴	N/A	2.5 × 10 ⁻⁴	N/A

Geometrical & Mechanical Specifications

Cladding Diameter	125.0 ± 1.0 μm	125.0 ± 1.0 μm	125.0 ± 1.0 μm	125.0 ± 1.0 μm
Core Diameter	5.0 μm	5.0 μm	6.0 μm	6.0 μm
Coating Diameter	245.0 ± 15.0 μm	245.0 ± 15.0 μm	245.0 ± 15.0 μm	245.0 ± 15.0 μm
Coating Concentricity	< 5.0 μm	< 5.0 μm	< 5.0 μm	< 5.0 μm
Core/Clad Offset	≤ 0.50 μm	≤ 0.50 μm	≤ 0.50 μm	≤ 0.50 μm
Coating Material	UV Cured, Dual Acrylate	UV Cured, Dual Acrylate	UV Cured, Dual Acrylate	UV Cured, Dual Acrylate
Operating Temperature Range	-55 to 85 °C	-55 to 85 °C	-55 to 85 °C	-55 to 85 °C
Proofstress Level	≥ 100 kpsi (0.7 GN/m ²)	≥ 100 kpsi (0.7 GN/m ²)	≥ 100 kpsi (0.7 GN/m ²)	≥ 100 kpsi (0.7 GN/m ²)



URL: <http://j-device.com>
 営業: sales@j-device.com
 TEL: 03-6262-3424
 FAX: 03-6800-5883

The passive version of each fiber is also available.
 Estimated value based on measured absorption @ 950 nm and 1010 nm for fibers PM-YSF-HI and SM-TSF-HI.



7 Airport Park Road, East Granby, CT 06026 • 860.408.5000 • Toll-free 866.466.0214 • Fax 860.844.0210 E-mail info@nufern.com • www.nufern.com • Nufern products are manufactured under an ISO 9001:2008 certified quality management system.

Standard specifications and design parameters are listed above. Specifications are subject to change without notice. Other configurations such as alternative form factors, optimized cut-off and UV cured color coating may be available. Let us know how Nufern can assist with your requirements.

Kokyo

株式会社光響
 Email: info@symphotony.com
 Web: <https://www.symphotony.com/>

NU0070- 11/07/2013

