

# 5/130 Ytterbium-Doped Double-Clad Fiber



Nufern's general purpose Ytterbium-Doped Double-Clad Fiber is available in two-versions — PANDA-style, polarization-maintaining (PM) and non-PM. Designed specifically for CW applications around 1-15 W, these fibers are ideal for applications requiring low-cost fiber laser and amplifier source, such as laser marking, fiber amplifier pumps and IR sources for frequency doubling. These fibers' telecom-type geometrics are compatible with readily available low-cost pump diodes and fiber-based components.

## Typical Applications

- Laser marking
- Fiber amplifier pumps
- IR sources for frequency doubling

## Features & Benefits

- NuCOAT™ fluoroacrylate coating — Greater fiber durability in extreme environmental operating & storage conditions
- Low cost double-clad technology — Enables use of high power multimode pump diodes
- Single-mode output — Compatible with standard telecom 980/1060 nm fiber-based components
- PANDA-style stress structure — Linearly polarized output for frequency conversion

## Optical Specifications

	PM-YDF-5/130-VIII	SM-YDF-5/130-VIII
Operating Wavelength	1060 – 1115 nm	1060 – 1115 nm
Core NA	0.120	0.120
First Cladding NA (5%)	≥ 0.46	≥ 0.46
Mode Field Diameter	6.5 ± 0.5 μm @ 1060 nm	6.5 ± 0.5 μm @ 1060 nm
Cutoff	950 ± 50 nm	950 ± 50 nm
Core Attenuation	≤ 15.0 dB/km @ 1200 nm	≤ 10.0 dB/km @ 1200 nm
Cladding Attenuation	≤ 15.0 dB/km @ 1095 nm	≤ 15.0 dB/km @ 1095 nm
Cladding Absorption	0.60 ± 0.10 dB/m at 915 nm 1.80 dB/m near 975 nm	0.55 ± 0.10 dB/m at 915 nm 1.65 dB/m near 975 nm
Birefringence	2.5 × 10 <sup>-4</sup>	N/A

## Geometrical & Mechanical Specifications

Cladding Diameter	130.0 ± 1.0 μm	N/A
Cladding Diameter (flat-to-flat)	N/A	130.0 ± 1.5 μm
Core Diameter	5.0 μm	5.0 μm
Coating Diameter	245.0 ± 10.0 μm	245.0 ± 10.0 μm
Coating Concentricity	< 5.0 μm	< 5.0 μm
Core/Clad Offset	≤ 1.00 μm	≤ 1.00 μm
Proof-test Level	≥ 100 kpsi (0.7 GN/m <sup>2</sup> )	≥ 100 kpsi (0.7 GN/m <sup>2</sup> )

The passive version of each fiber is also available - see PM-GDF-5/130 and SM-GDF-5/130



7 Airport Park Road, East Granby, CT 06026 • 860.408.5000 • Toll-free 866.466.0214 • Fax 860.844.0210 E-mail info@nufern.com • www.nufern.com • Nufern products are manufactured under an ISO 9001:2008 certified quality management system.

Standard specifications and design parameters are listed above. Specifications are subject to change without notice. Other configurations such as alternative form factors, optimized cut-off and UV cured color coating may be available. Let us know how Nufern can assist with your requirements.



**Kokyo**

株式会社光響  
Email : info@symphotony.com  
Web : https://www.symphotony.com/

NU0049- 11/07/2013

# 5/130 Passive Double Clad Fibers



Nufer's general purpose passive double-clad fiber is available in two-versions — PANDA-style, polarization-maintaining (PM) and non-PM. Designed specifically to work with 5/130 Yb-doped active fibers for CW applications at lower powers, ensuring low loss and improved splice compatability. These fibers' telecom-type geometrics are compatible with readily available low-cost pump diodes and fiber-based components. They utilize the latest fiber design and NuCOAT™ coating technology to ensure excellent preservation of beam quality and extended operating life demanded by today's industrial fiber laser applications.

## Typical Applications

- Laser marking
- Fiber amplifier pumps
- IR sources for frequency doubling

## Features & Benefits

- NuCOAT™ fluoroacrylate coating — Greater fiber durability in extreme environmental operating & storage conditions
- Low cost double-clad technology — Enables use of high power multimode pump diodes
- Single-mode output — Compatible with standard telecom 980/1060 nm fiber-based components
- PANDA-style stress structure — Linearly polarized output for frequency conversion"

## Optical Specifications

	PM-GDF-5/130	SM-GDF-5/130
Operating Wavelength	1060 – 1600 nm	1060 – 1600 nm
Core NA	0.120	0.120
First Cladding NA (5%)	≥ 0.46	≥ 0.46
Mode Field Diameter	6.5 ± 0.5 μm @ 1060 nm	6.5 ± 0.5 μm @ 1060 nm
Cutoff	950 ± 50 nm	950 ± 50 nm
Core Attenuation	≤ 10.0 dB/km @ 1200 nm	≤ 10.0 dB/km @ 1200 nm
Cladding Attenuation	≤ 15.0 dB/km @ 1095 nm	≤ 15.0 dB/km @ 1095 nm
Birefringence	2.5 × 10 <sup>-4</sup>	N/A

## Geometrical & Mechanical Specifications

	PM-GDF-5/130	SM-GDF-5/130
Cladding Diameter	130.0 ± 1.0 μm	130.0 ± 1.0 μm
Core Diameter	5.0 μm	5.0 μm
Coating Diameter	245.0 ± 10.0 μm	245.0 ± 10.0 μm
Coating Concentricity	< 5.0 μm	< 5.0 μm
Core/Clad Offset	≤ 1.00 μm	≤ 1.00 μm
Proofstress Level	≥ 100 kpsi (0.7 GN/m <sup>2</sup> )	≥ 100 kpsi (0.7 GN/m <sup>2</sup> )

The active version of each fiber is also available - see PM-YDF-5/130-VIII and SM-YDF-5/130-VIII



7 Airport Park Road, East Granby, CT 06026 • 860.408.5000 • Toll-free 866.466.0214 • Fax 860.844.0210 E-mail info @ nufern.com • www.nufern.com • Nufern products are manufactured under an ISO 9001:2008 certified quality management system.



Standard specifications and design parameters are listed above. Specifications are subject to change without notice. Other configurations such as alternative form factors, optimized cut-off and UV cured color coating may be available. Let us know how Nufern can assist with your requirements.