
SPECIALTY FIBER COPPER COATED FIBERS

LOW OH STEP INDEX MULTIMODE SILICA FIBERS

Copper-coated step index multimode optical fibers have significant improvements include increased mechanical strength and greater fatigue resistance compared to non-hermetic and polymer-clad fibers (PCS). Their transmittance covers a spectral range of 400 to 2200 nm, and also remains stable in corrosive chemicals that normally react to silica glass. The working temperature range is from -196°C to +600°C. Hermetically metal-coated optical fibers are the optimum candidate when used in high vacuum and harsh environmental conditions



FEATURES:

- Greatly enhanced resistance to high power laser radiation.
- Higher core-to-clad ratio and enlarged NA optimized for coupling to high-energy lasers.
- Better fiber cooling due to the heat-conducting metal coating.
- Excellent mechanical strength compared to polymer coated fibers.
- Solderable coating allows feeding the fibers into high vacuum systems and provides no outgassing.

FIBER SPECIFICATIONS	OK-50/125Cu	0K- 110/125Cu	0K- 200/220Cu	0K- 300/330Cu	OK- 400/440Cu	OK- 600/660Cu	OK- 800/880Cu	
Core diameter, µm	50 ± 3	113 ± 2	200 ± 2	300 ± 4	400 ± 5	600 ± 8	800 ± 10	
Clad diameter*, µm	125 ± 3	125 ± 2	220 ± 2	330 ± 4	440 ± 5	660 ± 8	880 ± 10	
Coating diameter, µm	160 ± 10	160 ± 10	280 ± 10	420 ± 10	545 ± 10	775 ± 10	980 ± 10	
Attenuation at 800/1300nm (see grapf Low OH)	14	The loss spectrum in the long wavelength region (>1 µm) is higher than that of the material			The loss spectrum is close to the material loss spectrum			
Wavelength range, nm (see grapf Low OH)	1000 ÷ 1600	400 ÷ 1100	400 ÷ 1700			400 ÷ 2200		
Fiber type	Multimode							
Index profile	Step							
Coating material	Copper 99,99%							
Core material	Pure syntetic silica (low OH)							
Clad material	Doped silica (F-doped)							
Numerical Aperture (NA)	0.16 ± 0.02 0.22 ± 0.02							
Short-term bending radius	60 times the fiber diameters							
Long-term bending radius	120 times the fiber diameters							
Proof test, kpsi	> 100							
Min operating temperature, °C	-196							
Max operating temperature (short time < 60s), °C	600							
Max operating temperature (long time > 60s), °C	< 400							

^{*}The core/clad ratios 1.06/1.1 on the request Other parameters are available on the request



Email: info@symphotony.com Web: https://www.symphotony.com/